

203/9 Dang Thuy Tram Str., Ward 13, Binh Thanh Dist., HCMC, Vietnam Tel: 84-8-35534001/2/3/4 Fax: 84-8-35534005/6 Email : info@lukivietnam.com

Website : www.lukivietnam.com

BIDIRECTIONAL FILAMENT TAPE

(LukiTape # 01106-01-125) Specs

Description

Lukitape#01106-01-125 Bidirectional Filament Adhesive Tape based on a polyester film laminated to cross weave fiber glass, which has a good tensile as well as high adhesion.

- It has a good longitudinal and transverse tensile strength as well as high tack and high strength.

- Ideal applications include bunding and strapping heavy goods, securing pallets and reinforce of shipping cartons.

- Remains good adhesion at wide temperature range(depends on the nature and the weight of the sealing materials.

Technical Characteristics

| Lukitape#01106-01-125 | |
|-------------------------------|---------------------------------|
| Total Thickness, microns | 135 |
| Backing | PET film |
| Reinforcement | Glass Yarn |
| Adhesive | Hot Melt Pressure Sensitive |
| Peel adhesion at 180°, N/25mm | 40 |
| Holding Power, hr/kg/24mm | >72 |
| Tensile Strength, N/25mm | 500 |
| Elongation (at break), % | 8 |
| Initial Adhesion | 14 |
| Storage life | 2 years from the date of making |
| Best temperature working | 15-35°C |

Standard Size

| Width | Length |
|-------------------|---------------------------|
| 24mm, 36mm, 48mm, | 30m, 40m, 50m, 66m, 100m, |
| 50mm, 60mm, 72mm | 1000m |

Core Size (ID): 1.5" and 3 "

Available in other sizes as well.

Storage Conditions: Store in a clean, cool and dry place, avoid sunshine direction. Storage at room temperature. If temperature approach 0° C, product will become harder.

IMPORTANT NOTICE

Luki makes no warranties, express or implied, including, but not limited to, any implied warranty or merchantability or fitness of a Luki product for a particular purpose. Luki is not responsible in determining the particular purpose or suitability of application on the user's behalf as the performance of the Luki product may vary under different applications and circumstances thereafter. The materials to be laminated with the product, the surface preparation procedures, choice of product, period of time and environment conditions when applied are factors which can affect the performance of the Luki product.

Given the countless number of possibilities which may affect the performance of the Luki's product, and some of which are within the user's knowledge and control, it is therefore essential for the user to determine whether the Luki's product is fit or suitable for that particular purpose or method of application. LIMITATION OF REMEDIES AND LIABILITIES

If the Luki's product is proven to be defective, THE EXCLUSIVE REMEDY, AT LUKI'S OPTION SHALL BE TO REFUND OR REPLACE THE DEFECTIVE Luki PRODUCT, and within the limits of the purchase price. Luki shall not otherwise be liable for any loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.